

THOMSON

DELPHION

RESEARCH

PRODUCTS

INSIDE DELPHION

My Account | Products

Search: Quick/Number Boolean Advanced

The Delphion Integrated View

Get Now: ☒ PDF | [More choices...](#)Tools: Add to Work File: [Create new Wo](#)View: INPADOC | Jump to: ☒ Go to: [Derwent...](#)☒ Email

Title: JP11260335A2: SEPARATOR FOR SEALED LEAD-ACID BATTERY

Country: JP Japan

Kind: A

Inventor: MATSUNAMI TAKAAKI;
AZUMATO YOSHIHISA;
KAWACHI MASAHIRO;Assignee: NIPPON MUKI CO LTD
[News, Profiles, Stocks and More about this company](#)

Published / Filed: 1999-09-24 / 1998-03-06

Application Number: JP1998000073095

IPC Code: H01M 2/16;

Priority Number: 1998-03-06 JP1998199873095

Abstract:

PROBLEM TO BE SOLVED: To reduce the thickness without deteriorating discharge characteristic and to improve the highly efficient discharge characteristic by impregnating a sheet prepared by a wet type sheet formation and principally constructed of glass fiber, with liquid dispersed with inorganic powder, and dispersingly arranging the inorganic powder grains between the glass fiber.

SOLUTION: As glass fiber, alkali-containing glass fiber with 0.5-4 μm of a mean fiber diameter is used. In wet type sheet formation of a sheet, principally consisting of glass fiber from average diameter glass fiber, either a composition consisting of glass fiber alone or a composition containing at most 5% of organic binder fiber to the separator weight may be used. Inorganic powder is uniformly dispersed over the entire surface and pores formed inside of a sheet formed of glass fiber principally to act to make labyrinth, complicating the porous structure of a separator. The quantity of the inorganic powder is set 5-50% vol.% of a pure volume of the separator, and preferably its grain diameter is smaller than that of the sheet and set to be 5 μm or less.

COPYRIGHT: (C)1999,JPO

Family: None

Other Abstract Info: CHEMABS 131(16)216520R CHEMABS 131(16)216520R DERABS C1999-596375 DERABS C1999-596375

